



**FOR SALES, SAMPLES OR  
TECHNICAL SERVICE**

Call 1-800-252-0039

1-423-629-7160

Fax 1-423-698-0614

Visit Sphere One at our website:  
[www.sphereone.net](http://www.sphereone.net)

## EXTENDOSPHERES™ SL-150 Hollow Spheres

EXTENDOSPHERES™ SL product lines increase the solid content of coating without the need for the addition of suspending agents. Self suspending microspheres are manufactured to reduce the VOC, which will result in lower shrinkage and reduced drying time.

The SL Extendspheres™ will improve abrasion resistance, modulus elongation, and the flow of paints resulting in a more durable coating. SL grades are an excellent choice for caulks, adhesives, paints, coatings, white roof and grouts.


### PACKAGING

EXTENDOSPHERES™ SL-150 is supplied in 50 lb multi-wall bags, 40 bags per pallet (2,000 lbs). Samples in sufficient quantity for testing are available upon request.

### SAFETY INFORMATION

In areas where these hollow spheres create a dust, the use of a NIOSH-approved mask or respirator is recommended. Material Safety Data Sheet (MSDS) will be supplied upon request.

TYPICAL PROPERTIES OF EXTENDOSPHERES™ SL-150 CERAMIC HOLLOW SPHERES	
Physical Form	Free-Flowing Powder
Appearance	Cream
Particle Size SL-150	Microns 10-150
Mean Particle Size SL-150	Microns 70
Bulk Density	21.5 lbs/ft <sup>3</sup>
Density	<0.62 +/- .03 g/cm <sup>3</sup>
Deformation Temperature	>1500°C
Compressive Strength	<10% @ 3000 psi
Hardness, Moh's Scale	5



Microtrac 3500S

The technical information presented herein represents the best information available to us and is believed to be reliable. Sphere One, Inc. makes no warranties, either expressed or implied, with respect to our materials, including the warranties of merchantability or fitness for any particular purpose. We urge that users of our materials conduct tests to determine suitability for their specific end uses.